

Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) **EP 1 217 047 A2**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
26.06.2002 Bulletin 2002/26

(51) Int Cl.7: **C09D 11/00**

(21) Application number: **01130416.9**

(22) Date of filing: **20.12.2001**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE TR**  
Designated Extension States:  
**AL LT LV MK RO SI**

(72) Inventors:  
• Rose, Peter Edward  
Winsford, Cheshire CW7 3EA (GB)  
• Thom, Jason Paul  
Northwich, Cheshire CW9 7DX (GB)  
• Walker, Nicholas Alexander  
Holmes Chapel, Cheshire CW4 8LS (GB)

(30) Priority: **23.12.2000 GB 0031644**

(71) Applicant: **ILFORD Imaging UK Limited  
Mobberley Knutsford Cheshire WA16 7JL (GB)**

(54) **Pigmented aqueous inks and ink set for ink jet printers**

(57) There is provided an aqueous ink jet ink composition comprising:

- (a) a black pigment which is carbon black; and
- (b) a blue pigment which is C.I. Pigment Blue 60; and
- (c) an aqueous carrier medium.

There is also provided a pigmented aqueous ink set comprising:-

- (a) A concentrated black ink having a pigment concentration up to 10% by weight; and

(b) at least one dilute ink having a pigment concentration below that of the concentrated ink;

wherein all the inks additionally comprise an aqueous carrier medium and at least one of the set of inks comprises a combination of carbon black and Pigment Blue 60.

EP 1 217 047 A2

**Description**Field of the Invention

- 5 [0001] This invention relates to improved black pigmented ink jet inks, and in particular to a black ink jet ink and an ink set showing an improved tonal appearance.

Background of the Invention

- 10 [0002] Ink jet printing is a non-impact method that in response to a digital signal produces droplets of ink that are deposited on a substrate such as paper or transparent film. Ink jet printers have found broad application as output for personal computers in the office and the home. There are several classes of ink jet printer, for instance thermal drop-on-demand printers, piezo drop-on-demand printers, and continuous ink jet printers.

- 15 [0003] Ink jet printers generally use aqueous inks, and such inks commonly employ dyes as colorants. Several suitable water soluble dyes which have been perfected for ink jet use are known, but there are some deficiencies to the use of these dyes. For instance they remain soluble in water on the printed page and are therefore subject to print defects such as feathering and to leaching by water, for example rain water and coffee. Furthermore, many of the dyes in use have poor light fastness and fade even on exposure to fluorescent lighting used in offices. There is particular difficulty in finding a good black dye to fulfil all these requirements and also provide a neutral black appearance. It is especially noticeable when printing monochrome, or so called black and white images, that grey areas of the image can appear somewhat blue, violet, or brown in shade rather than neutral. A blue shaded image is described as cold toned, and a brown shaded image as warm toned. Although under certain circumstances toned images may be desired, a neutral or nearly neutral shade is normally preferred, and it has become common to use a mixture of black dyes such as those disclosed in PCT WO 00/46309 partly in an attempt to provide the neutral appearance.

- 20 [0004] However the other difficulties remain, and consequently it is becoming increasingly common to use a black pigment such as carbon black in ink jet inks. The term pigment describes a colorant which is substantially insoluble in the aqueous ink medium. It is expected that prints produced using pigmented inks will display improved fastness to washing and weathering and better light stability. In addition carbon black shows a more neutral tone than dye based black inks.

- 30 [0005] There is interest in using ink jet prints as a replacement for conventional photographic monochrome, or black and white images. Monochrome prints cannot be produced to a high quality on a standard four colour ink jet printer. The alternatives for monochrome printing on a standard four colour printer are either to print a monochrome image using all four colours, or to print with the black ink only. Printing with coloured inks can result in a overall colour cast to the image, and in addition the individual coloured dots become visible in the light areas of the print. The alternative, printing with the black ink only, produces grainy prints because effectively the dot resolution of a 600 dpi (dots per inch) printer is reduced to 150 dpi, and this is most noticeable in the light areas of the print.

- 35 [0006] It is known that the use of more than one black ink (commonly four) of different dilutions (i.e. grey inks) can address these problems. For example it is known to use a conventional black ink in the "black" channel of the printer, and somewhat dilute black inks to feed the three colour channels, with the most dilute ink being in the "yellow" channel. Such inks may be printed without modification of the control software to produce a monochrome image. The use of all four ink cartridges allows full use of the dot resolution of the printer, but the image still suffers defects, for example that individual dots are visible in low density areas. Furthermore the overall image quality does not equal that of conventional photographic prints.

- 40 [0007] A rather better solution is to modify the controlling software and use four inks of increasing dilution. Such a system is commercially available under the trade name ILFORD Archiva MonoKrome Ink. By correct choice of the strength of each of the four inks and the design of the software a high quality image may be produced. Furthermore, the visibility of the dots in the light areas of the print can be reduced by printing such areas with light grey inks, thus increasing the number of dots printed for a given density and reducing the visual impact of any given dot, and the black density may be increased by overprinting one ink with another. One limitation of this approach however is that the image tone is dictated by the colour of the inks, and in particular that the lightest, or most dilute inks tend to provide brown, or warm toned images even though carbon black is used as pigment. This effect is the factor which limits the degree of dilution of the most dilute ink. On the other hand, it is generally desirable to increase the dilution of this ink to improve the image quality.

- 45 [0008] The use of a combination of carbon black with a dye in a black aqueous ink jet ink is known according to European Patent Applications 0 724 968 A, 0 913 438 A, and 1 002 839 A. The use of a combination of carbon black with cyan and magenta pigments is known according to United States Patent 5,803,958. However these inks are not described for improving the tone of black and white images. We have found a particular combination of pigments which is useful for providing monochrome images from aqueous ink jet inks.

Summary of the Invention


[0009] Therefore according to this invention there is provided an aqueous ink jet ink composition comprising:

- (a) a black pigment which is carbon black; and
- (b) a blue pigment which is C.I. Pigment Blue 60; and
- (c) an aqueous carrier medium.

[0010] Carbon black is listed in the Pigments and Solvent Dyes section of the Colour Index International, published by the Society of Dyers and Colourists in 1997 as C.I. Pigment Black 7. Examples include furnace black, lamp black, acetylene black, and channel black.

[0011] It is also possible to use a processed pigment such as self dispersing carbon black or graft carbon black having a surface treated with a resin or the like.

[0012] C.I. Pigment Blue 60 is an indanthrone of the following structure.



[0013] Optionally and preferably the ink may also comprise at least one dispersant for the pigments. The purpose of the dispersant is to stabilise the particles and prevent flocculation, aggregation, and settling of the ink. Suitable dispersants for pigmented ink jet inks are well known in the art, and include polymeric dispersants as well as some non-polymeric compounds of the surfactant type. Suitable dispersants for this invention include macromolecular polyionic dispersants, for example copolymers of styrene with acrylic, methacrylic, or maleic acids; various types of poly(ethylene oxide) condensates such as alkyl polyethylene oxide ethers and sulphate or phosphate esters thereof; and surfactants such as sarcosinate compounds. The ink may contain up to 400% of the dispersant by weight on the pigment, but preferably between about 10% and about 100% by weight on the pigment, and most preferably approximately 20 to 50% by weight on the pigment, depending on the pigment used and other properties desired of the ink.

[0014] A preferred dispersant for the inks of this invention is a copolymer of styrene with acrylic or methacrylic acids, together with optionally additional vinylically unsaturated comonomers such as acrylate esters. Preferably this dispersant is characterised by an acid number of between about 150 and about 250, a glass transition temperature between about 70° and about 100°, and a molecular weight of between about 2000 and about 20000, and most preferably the acid number is between 150 and 200 and the molecular weight is approximately 5000 - 15000. Many suitable styrene acrylate dispersants are commercially available. Such styrene acrylate copolymer dispersants may be supplied commercially in the form of concentrated solutions in aqueous base, or as solids which are to be dissolved in water in the presence of a base. Suitable bases for dissolving such dispersants include sodium or potassium hydroxide, ammonia, or an organic amine base such as ethanolamine, triethanolamine, 2-amino-2-methyl-1-propanol, or 1-(dimethylamino)-2-propanol. It is also possible to use mixtures of such bases to dissolve the styrene acrylate copolymer.

[0015] The pigment may be used in the form of a dry powder. However pigments are often supplied commercially as a concentrated aqueous pigment dispersion, and this invention is also useful for pigments supplied as such dispersions, which commonly include dispersants and other cosolvents as well as water. Alternatively the pigment may be supplied in the form of a water wet presscake. In presscake form, the pigment is not aggregated to the extent that it is in dry form and thus the pigment does not require as much deaggregation in the process of preparing the inks from dry pigments.

[0016] The ink may contain up to approximately 10% of each pigment by weight. The ratio of the black pigment to the blue pigment may be between 10:1 and 1:2, preferably between approximately 2:1 and approximately 1:1, by weight. The ratio depends on the particular grade of the black and blue pigment, the ink formulation, the printing medium,

and the desired final tone. The ratio may vary with the concentration of the pigments in the ink. In addition to providing neutral toned prints, controlled warm or cold toned prints may be produced by appropriately changing the pigment ratio.

**[0017]** By an aqueous carrier medium is meant a medium which is water or is predominantly water. It is common in aqueous ink jet inks to employ a carrier medium which is a mixture of water and at least one relatively involatile water soluble organic cosolvent. The purpose of the cosolvent is to act as humectant and prevent drying out of the ink in the nozzles of the printer, to improve printing performance, and also to improve the appearance of the final image. Deionised water is commonly used.

**[0018]** Preferably the ink comprises a mixture of water and at least one water soluble organic cosolvent. The water soluble organic cosolvent may be any organic solvent which has sufficient solubility in water. Representative examples of water-soluble organic solvents that may be selected include:

(1) alcohols, such as methyl alcohol, ethyl alcohol, n-propyl alcohol, isopropyl alcohol, n-butyl alcohol, sec-butyl alcohol, t-butyl alcohol, iso-butyl alcohol, neopentyl alcohol, benzyl alcohol, furfuryl alcohol, and tetrahydrofurfuryl alcohol;

(2) ketones or ketoalcohols such as acetone, methyl ethyl ketone and diacetone alcohol;

(3) ethers, such as tetrahydrofuran and dioxane;

(4) esters, such as ethyl lactate;

(5) polyhydric alcohols, such as ethylene glycol, diethylene glycol, triethylene glycol, tetraethylene glycol, polyethylene glycol, propylene glycol, dipropylene glycol, diacetone alcohol, trimethylolpropane, 2-methyl-2,4-pentanediol, 2,3,4-trimethyl-1,3-pentanediol, 1,3-propanediol, 1,5-pentanediol, glycerol, 1,2-hexanediol, and 1,2,6-hexanetriol;

(6) lower alkyl mono-or di-ethers derived from alkylene glycols, such as ethylene glycol monomethyl (or -ethyl) ether, diethylene glycol mono-methyl (or -ethyl) ether, propylene glycol mono-methyl (or -ethyl) ether, triethylene glycol mono-methyl (or -ethyl) ether and dichethylene glycol di-methyl (or -ethyl) ether;

(7) sulphur-containing compounds such as tetramethylene sulphone, dimethyl sulphoxide, and thiodiglycol; and

(8) nitrogen containing organic compounds such as 1,3-dimethyl imidazolidinone, urea, pyrrolidone and N-methyl-2-pyrrolidone.

**[0019]** Selection of a suitable mixture of water and water soluble organic cosolvent depends on the requirements of the specific application, such as the desired surface tension and viscosity, the selected pigment, the drying time of the pigmented ink jet ink, and the type of substrate onto which the ink will be printed. A mixture of water and at least one water soluble organic solvent having at least 2 hydroxyl groups is preferred. Therefore preferred organic cosolvents include for example diethylene glycol, triethylene glycol, polyethylene glycol, thiodiglycol, glycerol, 1,2-hexanediol, 1,5-pentanediol, and mixtures comprising these solvents. The aqueous ink composition may contain up to 50% of the organic cosolvent or mixture of organic cosolvents. Preferably the ink comprises up to 10% of each organic cosolvent, and most preferably between about 5% and about 10% of each of a mixture of at least two organic cosolvents.

**[0020]** The pigmented inks of the invention may also comprise other components which are advantageously added to aqueous ink jet inks, such as surfactants, viscosity modifiers, and biocides. In addition, sequestering agents such as EDTA may also be included to eliminate deleterious effects of heavy metal impurities. An additional colorant may also be present, but one of the advantages of the ink set of the invention is that a good image tone is provided using simple combinations of just two pigments.

**[0021]** It is generally desirable to prepare a concentrated dispersion by dispersing the pigment in water in the presence of one or more dispersants, and then to dilute this dispersion with additional water together with the organic solvent or solvents together with any other additives to form the ink. This technique permits preparation of a greater quantity of pigmented ink from the equipment. By dilution, the ink is adjusted to provide the desired concentration, colour strength, and other properties for the particular application. The surface tension is preferably in the range from about 30 dyne/cm to about 50 dyne/cm and the viscosity is generally no greater than 20 cP, and preferably in the range from about 1 cP to about 10 cP. Alternatively the cosolvent and any other additives may be present during the dispersion stage. The inks of the invention may either be prepared by dispersing the pigments separately to produce two separate dispersions and then combining them at dilution, or by dispersing a combination of the pigments.

**[0022]** The dispersing step may be accomplished by many well known methods, for example in a horizontal mini mill, a ball mill, a roll mill, an attritor, a homogeniser or by passing the mixture through a plurality of nozzles within a liquid jet interaction chamber at a liquid pressure of at least 1000 psi to produce a uniform dispersion of the pigment particles in the aqueous carrier medium.

**[0023]** The particle size of the pigment is preferably 10  $\mu\text{m}$  or less, particularly preferably 1  $\mu\text{m}$  or less and most preferably from 0.005 to 0.3  $\mu\text{m}$ .

**[0024]** According to another aspect of the invention there is provided an aqueous pigmented ink set for ink jet printers comprising two or more black inks of different concentration. Thus according to this aspect of the invention there is

provided a pigmented aqueous ink set comprising:-

- (a) A concentrated black ink having a pigment concentration of up to 10% by weight; and
- (b) at least one dilute ink having a pigment concentration below that of the concentrated ink;

wherein all the inks additionally comprise an aqueous carrier medium as herein before defined and at least one of the set of inks comprises a combination of carbon black and Pigment Blue 60.

[0025] Thus according to this aspect of the invention there is provided a black ink of greatest concentration and at least one dilute black ink, that is to say grey ink of lower concentration. Preferably the pigment concentration in the black ink is between about 3% and about 5%.

[0026] Preferably according to this aspect of the invention there is provided a pigmented aqueous ink set of four inks comprising:-

- (a) A concentrated ink having a pigment concentration between about 3% and 5% by weight;
- (b) a dilute ink having a pigment concentration between about 1% and about 4% by weight;
- (c) a more dilute ink having a pigment concentration between about 0.5% and about 3% by weight; and
- (d) a most dilute ink having a pigment concentration between about 0.1% and about 1% by weight;

wherein all the inks additionally comprise an aqueous carrier medium as herein before defined and at least one of the inks comprises a combination of carbon black and Pigment Blue 60.

[0027] It is to be understood that the preferred pigment concentration of each of the inks depends on the controlling software as well as the printer to be used, the type of substrate onto which the ink will be printed, and the desired visual result. However in general the preferred pigment concentration of the black ink (a) is approximately 3-5%, that of the second ink (b) is between 1% and 3%, that of the third ink (c) between 0.5% and 2%, and that of the most dilute ink (d) between 0.1% and 0.8%. Most preferably the three dilute inks all comprise the combination of carbon black and Pigment Blue 60. The weight ratio between the carbon black and Pigment Blue 60 may be different in the different inks of the ink set. For certain uses it is preferable that the proportion of blue pigment will be greater in the ink or inks of lowest concentration.

[0028] The inks of the pigmented ink set of this aspect of the invention may advantageously also comprise other components as herein before defined such as a dispersant.

[0029] The ink set of this aspect of the invention produces pleasing high quality images of good image tone and high maximum density but showing minimum dot visibility in the highlight areas of the print. A further advantage of the inks of the present invention is that the prints exhibit excellent lightfastness.

[0030] In another embodiment of the present invention, there is provided a process of printing using the ink and ink set of the invention. The printing is effected by using the ink set in an ink jet printer, and applying the ink to a printing medium which can be any of the substrates commonly used for ink-jet printing, for example so-called plain paper, coated paper, wet strength paper, fine art paper, canvas, self-adhesive vinyl, scrim vinyl, overhead transparencies, fabrics, and synthetic media such as white polyester and bonded nonwoven polyolefin film-fibril sheets such as polyethylene or polypropylene banner materials.

[0031] The inks and ink set of this invention may be used with a variety of ink jet printers such as continuous, piezoelectric drop-on-demand and thermal or bubble jet drop-on-demand, and are particularly adapted for use in piezoelectric and thermal drop on demand printers. The printer may be a desk top printer or a wide format ink jet printer.

[0032] The stability of the ink formulation also allows long storage periods without any loss of printability.

[0033] The following examples will serve to illustrate the invention:

#### Example 1.

[0034] A comparative ink set was prepared as follows:

#### Preparation of Black Pigment Dispersion

[0035] A black pigment dispersion according to the composition shown in Table 1 was prepared using a Microfluidiser Model M210C at 30,000psi. The dispersion was then centrifuged to remove oversized particles. A commercial sample of Carbon Black pigment was used available from Degussa - Hüls under the trade name Black S170. The dispersant used was a commercially available styrene acrylate copolymer having an acid number of 190, a Tg of 70° and a molecular weight of 2000 to 6000 neutralised with potassium hydroxide. This dispersant is available from BF Goodrich.

# EP 1 217 047 A2

Table 1.

Component	% by weight
Carbon Black Pigment	10
Dispersant	2.5
Deionised Water to make	100

[0036] The average particle size of the dispersion was less than 200nm.

## Preparation of inks

[0037] Three black inks with decreasing concentration were prepared from the black dispersion by dilution according to the formulations shown in table 2.

Table 2.

Component	Amount Parts by Weight		
	Ink 1	Ink 2	Ink 3
Black Pigment Dispersion	15	8.5	5.0
Thiodiglycol	10	10	10
Urea	5	5	5
Polyethylene Glycol MW300	5	5	5
Diethanolamine	0.4	0.4	0.4
Deionised Water to make	100	100	100

[0038] An ink set according to the invention was prepared as follows:

## Preparation of Blue Pigment Dispersion

[0039] A blue pigment dispersion according to the composition shown in Table 3 was prepared using a Microfluidiser Model MI 10 at 12000psi. A commercial sample of Pigment Blue 60 from Dainippon Ink and Chemicals under the trade name Fastogen Super Blue 6070S was used. The dispersant used was a commercially available styrene acrylate copolymer having an acid number of 215, a Tg of 95° and a molecular weight of 8500 neutralised with potassium hydroxide. This dispersant is available from SC Johnson Polymers. The dispersion was then centrifuged at 3000 rpm for 20 minutes to remove oversized particles.

Table 3.

Component	% by weight
Pigment Blue 60	7.14
Dispersant	3.57
Deionised Water to make	100

## Preparation of inks

[0040] Three inventive black inks were prepared by adding this blue pigment dispersion to the black inks 1-3 according to the formulations shown in table 4.

Table 4.

Component	Amount Parts by Weight		
	Ink 4	Ink 5	Ink 6
Black ink 1	50		
Black ink 2		50	
Black Ink 3			50
Blue Pigment Dispersion	6.2	3.5	2.1
Total	56.2	53.5	52.1
Total Pigment Concentration	2.39%	1.35%	0.8%
Ratio black:blue pigment	1.7:1	1.7:1	1.67:1

### Colorimetry

[0041] The comparative and inventive inksets were loaded into an Encad Novajet 700i Inkjet printer. Test charts including 100% density patches were printed on ILFORD IJP1GP7 media. All inks printed successfully and produced excellent image quality. The Density and CIELAB L\* a\* b\* colorimetry values of the 100% density patches of the prints were measured with a Gretag Specrolino reflectance colorimeter using D65 illuminant and 2° Standard Observer. The results are shown in Table 5.

Table 5.

		CIELAB colorimetry values		
		L*	a*	b*
Inkset 1 (Comparative)	Ink 1	20.91	0.77	0.42
	Ink 2	32.82	1.85	6.17
	Ink 3	45.7	1.72	6.79
Inkset 2 (Inventive)	Ink 4	32.13	-0.11	-0.55
	Ink 5	36.5	-0.37	0.84
	Ink 6	51.59	-0.23	1.35

[0042] Under the L\* a\* b\* colorimetry system the a\* value is a measure of the colour along the green/red axis, with a negative value being greener, and the b\* value is a measure of the colour along the blue/yellow axis, i.e. warm or cold toned, with a negative value being bluer or cold toned. A neutral tone has both a\* and b\* zero. It is seen that the two more dilute comparison inks 2 and 3 show a very strong and unpleasant brown or warm tone, with the b\* value significantly removed from neutrality and also quite a positive a\* value, whereas the inks from the inventive ink set display a nearly neutral tone. The b\* and a\* values of the inventive inks are sufficiently close to zero that the prints appear visually neutral.

### Print Test

[0043] A comparison ink set comprising four inks of different dilution was made up comprising a black ink having a concentration of 3.5% carbon black and no blue pigment together with the comparison inks 1, 2, and 3 prepared above. An inventive ink set was also made up comprising the same black ink and the inventive inks 4, 5, and 6. A monochrome image was printed on ILFORD matt bond paper UMBP6 with each set using an ILFORD MonoKrome system. A high quality image of good gradation was produced by both ink sets, but that from the comparison inks was visually warm toned and that of the inventive set was visually neutral.

Claims

1. An aqueous ink jet ink composition which comprises:-

- (a) a black pigment which is carbon black; and
- (b) a blue pigment which is C.I. Pigment Blue 60; and
- (c) an aqueous carrier medium.

2. An aqueous ink jet ink composition according to claim 1 wherein the aqueous carrier medium comprises water and at least one water soluble organic cosolvent.

3. An aqueous ink jet ink composition according to claim 2 wherein the organic cosolvent is selected from diethylene glycol, polyethylene glycol, thiodiglycol, glycerol, urea, pyrrolidone, and combinations thereof.

4. An aqueous ink jet ink composition according to any of claims 1 - 3 which additionally comprises at least one dispersant.

5. An aqueous ink jet ink composition according to claim 4 wherein the dispersant is a styrene/acrylate copolymer.

6. A pigmented aqueous ink set comprising:-

- (a) a concentrated black ink having a pigment concentration of up to 10% by weight; and
- (b) at least one dilute ink having a pigment concentration below that of the concentrated ink;

wherein all the inks additionally comprise an aqueous carrier medium and at least one of the set of inks comprises carbon black and Pigment Blue 60.


7. A pigmented aqueous ink set comprising:-

- (a) a concentrated ink having a pigment concentration between 3% and 5% by weight;
- (b) a dilute ink having a pigment concentration between 1% and 4% by weight;
- (c) a more dilute ink having a pigment concentration between 0.5% and 3% by weight; and
- (d) a most dilute ink having a pigment concentration between 0.1% and 1% by weight;

wherein all the inks additionally comprise an aqueous carrier medium and at least one of the inks comprises carbon black and Pigment Blue 60.

8. A process for printing which comprises using the ink jet ink set of claim 6 or 7 in an ink jet printer, and applying the ink to a printing medium with the ink jet printer.





Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11)

**EP 1 217 047 A3**

(12)

**EUROPEAN PATENT APPLICATION**

(88) Date of publication A3:  
17.09.2003 Bulletin 2003/38

(51) Int Cl.7: **C09D 11/00**

(43) Date of publication A2:  
26.06.2002 Bulletin 2002/26

(21) Application number: **01130416.9**

(22) Date of filing: **20.12.2001**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE TR**  
Designated Extension States:  
**AL LT LV MK RO SI**

(30) Priority: **23.12.2000 GB 0031644**

(71) Applicant: **ILFORD Imaging UK Limited  
Mobberley Knutsford Cheshire WA16 7JL (GB)**

(72) Inventors:  
• **Rose, Peter Edward**  
Winsford, Cheshire CW7 3EA (GB)  
• **Thom, Jason Paul**  
Northwich, Cheshire CW9 7DX (GB)  
• **Walker, Nicholas Alexander**  
Holmes Chapel, Cheshire CW4 8LS (GB)

(54) **Pigmented aqueous inks and ink set for ink jet printers**

(57) There is provided an aqueous ink jet ink composition comprising:

- (a) a black pigment which is carbon black; and
- (b) a blue pigment which is C.I. Pigment Blue 60; and
- (c) an aqueous carrier medium.

There is also provided a pigmented aqueous ink set comprising:-

- (a) A concentrated black ink having a pigment concentration up to 10% by weight; and

(b) at least one dilute ink having a pigment concentration below that of the concentrated ink;

wherein all the inks additionally comprise an aqueous carrier medium and at least one of the set of inks comprises a combination of carbon black and Pigment Blue 60.

**EP 1 217 047 A3**



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 01 13 0416

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	EP 0 899 311 A (SEIKO EPSON CORP) 3 March 1999 (1999-03-03) * page 2, line 33 - line 43 *	1-5	C09D11/00
Y	* page 3, line 3 - line 17 * * page 3, line 43 - line 46 * * page 4, line 48 - line 55 * * page 6, line 13 - line 21 *	6-8	
Y	PATENT ABSTRACTS OF JAPAN vol. 2000, no. 01, 31 January 2000 (2000-01-31) & JP 11 286126 A (CANON INC), 19 October 1999 (1999-10-19)	6-8	
A	* abstract * & ANONYMOUS: INTERNET ARTICLE, 'Online! Retrieved from the Internet: <URL:http://www19.ipdl.jpo.go.jp/PA1/resul t/detail/main/WAAAsLa4nWDA411286126P1.htm> 'retrieved on 2003-07-24! COMPUTER TRANSLATION * paragraphs '0007!', '0010!', '0031!'-'0033!', '0048!'-'0055! * & US 6 342 096 B1 (CANON KABUSHIKI KAISHA) 29 January 2002 (2002-01-29) * column 2, line 59 - line 66 * * column 3, line 46 - line 66 * * column 18, line 23 - line 63 * * examples 1,2 *	1-5	TECHNICAL FIELDS SEARCHED (Int.Cl.7) C09D
A	US 6 030 440 A (KIYOTA KOHEI ET AL) 29 February 2000 (2000-02-29) * column 3, line 20 - line 24 * * column 4, line 1 - line 16 * * table 4 *	1-5	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 25 July 2003	Examiner Matthijssen, J-J
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons &amp; : member of the same patent family, corresponding document</p>			

EPO FORM 1503 33/82 (P/Cat1)

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 13 0416

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

25-07-2003

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
EP 0899311	A	03-03-1999	JP	11061022 A	05-03-1999
			DE	69809510 D1	02-01-2003
			EP	0899311 A1	03-03-1999
			US	2002017219 A1	14-02-2002
JP 11286126	A	19-10-1999	US	6342096 B1	29-01-2002
US 6030440	A	29-02-2000	JP	11181342 A	06-07-1999
			DE	19808672 A1	01-07-1999
			DE	19861069 A1	18-11-1999

EPO FORM P0455

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**THIS PAGE BLANK (USPTO)**